

Technical Data Sheet (TDS)

rPP

rPP Injection Grade - Natural (MFR 6)

Type: PIR- Post Industrial Recycled Polypropylene



Special Characteristics: rPP Injection Grade – Natural Color (MFR 6) is PIR- Post Industrial Polypropylene material. They are used for Injection Applications.

Typical Applications: Injection Applications, Masterbatch

Properties	PP Recycle Injection Grade - Natural	Unit	Test Method
Melt Flow Rate (230 °C, 2.16 kg)	6	g/10 min	ASTM D1238

Recommendation (Injection Application):

The recommended temperature setting is in the range of 190 -240 °C

Note: Typical properties: these are not to be construed as specifications.

Disclaimer: The information presented herein, while not guaranteed, is, to the best of our knowledge true and accurate. No warranty or guarantee, express or implied, is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control.